

INOX Solder Oil

Cat.-No. 2444

Flux based on zinc ammonium chloride

Type 3.1.1.A under ISO 9454

Customer added value

- Ready-to-use soft-solder flux with great heat stability
- Very good solder properties even in difficult application areas
- Very highly activated
- Residues easily dissolved in water



Technical data

Appearance	colourless to light brown, transparent, low viscosity
Density at 20 °C	about 2.0 g/cm ³
Durability:	24 months
Water solubility:	easily
Debris:	must be removed

Application area

Conventional soft-soldering of stainless steel, iron, copper, and brass materials

Packaging units

- | | | |
|--|---|--|
| <input checked="" type="checkbox"/> canister / 1000 ml | <input type="checkbox"/> Metering bottle / ml | <input type="checkbox"/> Spray bottle / ml |
| <input type="checkbox"/> Granulate / Size | <input type="checkbox"/> Metering pen / ml | <input type="checkbox"/> Injection / ml |

EMIL OTTO Flux- und Oberflächentechnik GmbH
 D-65346 Eltville – Eltviller Landstr. 22
 Tel.: +49 (0)6123 / 70 46 0 – Fax: +49 (0)6123 / 70 46 15



The data given in our descriptions are typical values. They are provided for your information, but do not represent specifications or assurances of properties in the sense of liability and warranty claims. The same applies to the application-related information; these are non-binding and do not release our customers from their own testing of our products for their suitability for the intended purpose Process or purpose.